

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Original) A heat resistant magnesium die casting alloy comprising, by wt%, the following composition:

Al: over 6% to not more than 10%,

Ca: 1.8 to 5%,

Sr: 0.05 to 1.0%,

Mn: 0.1 to 0.6%, and

Bal: Mg and unavoidable impurities,

the ratio Ca/Al of the Ca content to the Al content being 0.3 to 0.5.

2. (Original) A heat resistant magnesium die casting alloy as set forth in claim 1, wherein Ca: over 2% to not more than 5%.

3. (Original) A heat resistant magnesium die casting alloy as set forth in claim 1, wherein Ca: 2.5 to 3.5%.

4. (Currently Amended) A heat resistant magnesium die casting alloy as set forth in ~~any one of claims 1 to 3~~claim 1, further comprising a rare earth metal in an amount of 0.1 to 3 wt%.

5. (Currently Amended) A die cast product comprised of a magnesium alloy as set forth in ~~any one of claims 1 to 4~~claim 1.

6. (New) A heat resistant magnesium die casting alloy as set forth in claim 2, further comprising a rare earth metal in an amount of 0.1 to 3 wt%.

7. (New) A heat resistant magnesium die casting alloy as set forth in claim 3, further comprising a rare earth metal in an amount of 0.1 to 3 wt%.

8. (New) A die cast product comprised of a magnesium alloy as set forth in claim 2.

9. (New) A die cast product comprised of a magnesium alloy as set forth in claim 3.

10. (New) A die cast product comprised of a magnesium alloy as set forth in claim 4.